

Product Description

OBEX CORTEX 0901 EPDM Corner is an external preformed EPDM Corner to be used when bonding EPDM membrane around windows and curtain walling applications to create a weathertight seal.

Technical Data

Properties	Specification	Typical result
Colour	Black	N/A
Hardness (IRHD)	60-70	65
Tensile strength (Mpa)	10-15	11
Elongation at break (%)	300-500	450
Compression set (%) 24hrs at 70°C	20-50	25
Tear strength (kg/cm)	10-20	11
Heat aged 70hrs at 70°C		
Hardness change (IRHD)	+10 Max	+3
Change in tensile strength (%)	-20 Max	-5
Change in elongation at break (%)	-35 Max	-5

Post Cure Parameters

2 hours @ 140°C.